

NO. 600 FLAKE CAPPING COMPOUND

DESCRIPTION

Sauereisen No. 600 flake style Basolit Sulfur Capping Compound has been used for many years by the concrete testing laboratories for testing concrete cylinders for comprehensive strength.

OUTSTANDING CHARACTERISTICS

No. 600 is supplied in flake form and provides exceptionally easy and convenient handling and melting compared to blocks or briquets. No. 600 is consistent from one bag to the next which ensures high strength from cap to cap.

No. 600 is carefully plasticized to provide even load distribution during compression testing with no deformation. It sets rapidly to exhibit a minimum compressive strength of 8000 psi after cooling two hours, in accordance with requirements of ASTM C-617, Standard Method of Capping Cylindrical Concrete Specimens.

No. 600 has a wide pouring range: if accidentally overheated, it remains usable when cooled to the proper temperature (excess poured and solidified material can be remelted without loss of properties).

No. 600 maintains its full compressive strength and bond to concrete even when capped specimens are stored at 100% relative humidity prior to testing and does not degrade during storage or use.



APPLICATION

Temperature of Capping Plate: Maintain an optimum temperature of 85°F to 90°F on the capping plate to prevent thermal shock and potential cracking when molten material is poured into the capping plate.

Capping Plate Preparation: Capping plates should be lightly coated with mineral oil prior to No. 600 application.

Melting: Use a suitable melting pot for sulfur-base compounds equipped with automatic temperature controls. Empty quantity of No. 600 into melting pot and regulate temperature between 265°F and 290°F. Melt material in this temperature range to a smooth, free-flowing liquid. If heated above 300°F, the material thickens. To reduce viscosity and lower the temperature to optimum range, remove the heating element and/or add more No. 600 material. Overheated material is still usable after temperature has decreased to 265°F-290°F, provided temperature has not exceeded 320°F.

Installation: Pour the molten No. 600 into the capping plate with a ladle. Place the concrete cylinder immediately into the sulfur cement and allow to remain until the compound solidifies (approximately one minute). After the compound has solidified, remove the cylinder from the mold. Allow a minimum of 2 hours after hardening before crushing capped specimens. Unused material left in the melting kettle can be removed by chipping after it has been cooled and then reused.

SPECIFICATIONS

- | | | |
|--|--|-----------------------------------|
| • Material:
Sulfur-based compound; silica-filled | • Optimum Pouring Range:
265°F - 290°F | • Melting Range:
230°F - 240°F |
| • Compressive Strength
9,000 psi (ASTM C-579)
8,000 psi (ASTM C-617) | • Packaging:
50 lb. moisture-resistant bags
(or pails for small shipments) | • Set Time:
Approx. 1 min. |

For a free sample, competitive price quote, or to place an order, Call us...

J.A. CRAWFORD CO.

...since 1967

(800) 223-5883

Corporate Office and Warehouse:

11813 East Slauson Ave., Santa Fe Springs, CA 90670
Phone: (562) 698-0901 • Fax: (562) 696-8761